

# LOCTITE<sup>®</sup> SI 5300<sup>™</sup>

November 2019

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> SI 5300<sup>™</sup> provides the following product characteristics:

<b>Technology</b>	Silicone
<b>Chemical Type</b>	Acetoxy silicone
<b>Appearance (uncured)</b>	Red paste <sup>LMS</sup>
<b>Components</b>	One component - requires no mixing
<b>Thixotropic</b>	Reduced migration of liquid product after application to substrate
<b>Cure</b>	Room temperature vulcanizing (RTV)
<b>Application</b>	Bonding or Sealing

LOCTITE<sup>®</sup> SI 5300<sup>™</sup> is generally used for sealing applications, but also for bonding and for high temperature protection. It is primarily used in industrial bonding/sealing applications, heating engineering, industrial ovens, household electrical and industrial heating equipment. This product is typically used in applications up to 350 °C.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.05
Extrusion Rate, g/min:	
Pressure 0.62 MPa, time 15seconds, temperature 25 °C:	
Semco Cartridge	250

Flash Point - See SDS

## TYPICAL CURING PERFORMANCE


### Surface Cure

Cured @ 22°C, 50% RH

Skin Over Time, min	8
---------------------	---

## Cure Speed

The graph below shows the shear strength developed over time at 22 °C / 50 % RH on Aluminum and tested according to ISO 4587.



## TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 21 days @ 22 °C / 50% RH

### Physical Properties:

Shore Hardness, ISO 868, Durometer A	31
Linear Shrinkage, %	0.32
Volume Shrinkage, %	0.97
Coefficient of Thermal Expansion, ISO 11359-2, K <sup>-1</sup>	330×10 <sup>-6</sup>
Coefficient of Thermal Conductivity ISO 8302, W/(m·K)	0.63
Tensile Strength, ISO 37	N/mm <sup>2</sup> 1.6
Tensile ModulusN/mm <sup>2</sup> ,	1.0
Elongation, at break, ISO 37, %	≥260

### Electrical Properties:

Surface Resistivity, IEC 60093, ΩPΩ	51
Volume Resistivity, IEC 60093, TΩ·cm	1.1

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Adhesive Properties

After 21 days @ 22 °C / 50% RH

Lap Shear Strength, ISO 4587 MPa:	
Aluminum (Gritblasted)	0.96
Aluminum (Alclad)	0.97
Mild steel	0.31
Mild steel (grit blasted)	0.76
Stainless steel	0.48
Nylon	0.8

Silicone rubber	0.54
Phenolic	1.17
PET	0.63
Zinc plated steel	0.24
Steel (e-coated)	0.77

### TYPICAL ENVIRONMENTAL RESISTANCE


Cured for 21 days @ 22 °C / 50% RH

Lap Shear Strength, ISO 4587:

Aluminum (grit blasted)


#### Hot Strength

Tested at temperature



#### Heat Aging

Aged at temperature indicated and tested @ 22 °C



#### Chemical/Solvent Resistance

Aged under conditions indicated and tested @ 22 °C.

Environment	°C	% of initial strength		
		100 h	500 h	1000 h
Water/glycol 50/50	100	105	105	105
Water/glycol 50/50	120	90	85	85
ATF	120	65	55	55
Mineral Oil	150	70	45	45
Synthetic oil	120	90	70	60
Synthetic oil	150	80	35	20
Water	60	110	120	105
Water	90	100	90	85

### GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

NOTE: *This product is not recommended for contact with gasoline.*

#### Directions for use:

1. For best performance bond surfaces should be clean and free from grease.
2. Moisture curing begins immediately after the product is exposed to the atmosphere, therefore parts to be assembled should be mated within a few minutes after the product is dispensed.
3. The bond should be allowed to cure before subjecting to heavy service loads.
4. Excess material can be easily wiped away with non-polar solvents.
5. For full automatic applications a volumetric dispensing system is recommended.

#### Loctite Material Specification<sup>LMS</sup>

LMS dated April 02, 2011. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

#### Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

#### Conversions

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\mu\text{m} / 25.4 = \text{mil}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{N/mm}^2 \times 145 = \text{psi}$$

$$\text{MPa} \times 145 = \text{psi}$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

#### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our



knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.1